

BETASEAL™ U-418

Glass Bonding Systems

BETASEAL™ U-418 is a one-component, fast-curing, high viscosity adhesive suitable for stationary glass bonding and is primerless to most glass substrates. It is resistant to extended outdoor weathering without losing its adhesion and physical characteristics.

Product information

Colour	Black -
Density	1190 kg/m³
Solid content	≥94 %

Cured properties

Stress at break	4.8 MPa	DIN 53504
Strain at break	400 %	DIN 53504
Lap shear strength, 3 days	≥3.45 MPa	DIN EN 1465
Shore hardness A	55 - 60 -	DIN 53505

Application technique

Tack free time 15 - 35 min

Characteristics

Delivery form Cartridges, Sausages

Compatibility Glass

Revised: 2020-05-20 Page: 1 of 1

dupont.com



DuPont[™], the DuPont Oval Logo, and all trademarks and service marks denoted with [™], SM or [®] are owned by affiliates of DuPont de Nemours. Inc. unless otherwise noted. © 2020 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-4 and DuPont CAUTION Regarding Medical Applications H-50102-4.