

Technical Information

1 Product Name

QwikSet Mirro-Mastic®

2 Manufacturer

Palmer Products Corporation
146 St. Matthews Ave.
Louisville, KY 40207

Phone

800.431.6151
502.893.3668

Fax

502.895.9253

Website

mirro-mastic.com

E-mail

palmer@mirro-mastic.com

3 Product Description

Basic Use

QwikSet Mirro-Mastic® is a high quality, fast curing, adhesive mastic formulated for adhering plate glass mirror to various substrates.

Note: Do not use on acrylic mirror or safety backings.

4 Technical Data

Appearance

Viscous liquid

Application temperature

59°F to 95°F (15°C to 35°C)

Cleanup

Mineral spirits

Color

Black

Composition and materials

QwikSet is a rubber base adhesive

Coverage

With **minimum** coverage, one 10.1 fl oz (300 ml) cartridge will install approximately 20 square feet (1.9 square meters) of mirror

Curing time

Curing time will depend on temperature, humidity, type of substrate and amount of air that can reach the mastic

Density

8.300 – 8.700 lb/gal

Flash point

64.4°F (18°C)

Packaging

10.1 fl oz (300 ml) per cartridge (24 per case)

Shelf Life

One year from the production date for an unopened cartridge

Storage

50°F to 85°F (10°C to 29.4°C)

Viscosity

No data available

VOC Content

293 g/L

WARNING: All Palmer products must be used only for approved purposes, and must be applied only in accordance with Palmer's installation instructions. The user bears all risk of damage, injury or other loss arising out of any nonapproved use and/or improper installation of any Palmer product. If Palmer's installation instructions are not followed, in whole or part, for whatever reason, then mechanical fasteners of sufficient size and strength must immediately be used to insure safety of the installation pending prompt proper reinstallation by the product user. Any failure to properly utilize or apply any Palmer product may result in property damage, bodily injury or death. Palmer shall not be responsible for these or any other types of misuse of its products.